

LESONAL®

MULTI MATT CLEAR



**KEEP AHEAD
OF THE MARKET**

GREAT FINISH. FAST.

VERSATILITY AND QUALITY THAT OUTPERFORM THE COMPETITION

Designed for the refurbishment or total re-spray of original matt finish cars and car parts, Lesonal Multi Matt Clear brings flexibility and long-lasting reliability to bodyshops. It gives users the ability to match any gloss level, while ensuring a consistent appearance and no cloudiness.

VERSATILE SYSTEM

The two mixable A-components, Low Gloss and Semi Gloss, can be blended to achieve the exact gloss level required, by using the Multi Matt Swatch, the original gloss level can be determined quickly.

PREMIUM FINISH

Enjoy a consistent application and robust results that eliminate cloudiness with ease. As well as being simple to prepare, Multi Matt Clear has excellent durability, achieving a smooth, robust and long-lasting finish with only minimum increase in gloss over time.

Multi Matt Clear provides a versatile, user-friendly, high-quality alternative to existing regular matt clearcoats, matt pastes and other matting products in the market.

COMPACT SYSTEM

Through our clever portfolio of products, a choice of two reducers – Reducer Standard and Reducer Slow – enables painters to adapt to the size of the job, whether it involves spraying the whole car body or an individual panel.

FEATURES	BENEFITS
Multi matt concept	Produce any desired gloss level
Easy and consistent application	Even and cloud-free appearance
State-of-the-art technology	Smooth, hard finish with minimum increase in gloss over time Long-term customer satisfaction
Multi Matt Swatch	Quickly determine original gloss level and correct mix for a good match
Compact assortment	Flexibility for all sizes of jobs under all conditions

VERSATILE

Perfection in every finish, whatever gloss level is required

PREMIUM

Cloud-free appearance coupled with a smooth and robust surface

COMPACT


Cover all type of repairs with just two reducers



QUICK REFERENCE GUIDE


MULTI MATT CLEAR

Mixing Ratio



5 Multi Matt Clear
2 Multi Matt Clear Hardener
3 Multi Matt Clear Reducer Standard / Slow

Mixing stick



S

Equipment



Spray gun set-up:
1.3-1.4 mm


Application pressure:
1.7-2.2 bar at the air inlet
HVLP max 0.6-0.7 bar at the air cap

Application



2 x 1 coat

Flash-off



Between coats:
15 mins at 20°C

Before curing:
15 mins at 20°C

Drying time



Low Gloss
Semi Gloss

40°C
1 hrs
1,5 hrs

60°C
15 mins
20 mins

Protection



Use suitable respiratory protection
Akzo Nobel Car Refinishes recommends the use of fresh air supply respirator

For a perfect matt finish, visit www.lesonal.uk